stomdevice

HARZ Labs
MATERIALS FOR 3D PRINTING

HARZ Labs
Dental Cast Cherry

Material Technical Data Sheet (TDS)

Version 1.2 / EN
13 April 2021

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ

stomdevice

SECTION 1: DESCRIPTION AND APPLICATION

Dental Cast Cherry is intended for direct casting of dental implants such as metal crowns, bridges, clasp dentures.

SECTION 2: MATERIAL PROPERTIES

2.1 Characteristics of liquid

Tested property	Standard/Method	Result
Color	-	Cherry (semitransparent)
Odor	-	Weak
Density	ASTM D1298	1.1 ± 0.1 g/cm^3
Viscosity (25 °C)	ASTM D2393	200 ± 100 mPa

2.2 Mechanical properties

Tested property	Standard/Method	Result
Flexural Strength	ASTM D790	75.0 ± 5.0 MPa
Flexural Modulus	ASTM D790	1000 ± 100 MPa
Ultimate Tensile Strength	ASTM D638	45.0 ± 5.0 MPa
Elongation at Break	ASTM D638	7.0 ± 3.0 %
Hardness	ASTM D2240	75.0 ± 5.0 Shore D
IZOD Impact (Unnotched)	ASTM D4812	4.0 ± 1.0 kJ/m^2

2.3 Special parameters

Tested property	Standard/Method	Result
Solubility (24h)	ASTM D3132	≤ 0.01 %
Sorption (24h)	ASTM D570	≤ 0.47 %
Ash content	ASTM D5630	< 0.1 %

The information above is believed to be accurate and represents the best information currently available to us. All test specimens were printed, cleaned, and post-processed per instructions provided by HARZ Labs company. Results provided here are representative of these processes and may vary if these established protocols are not followed. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall HARZ Labs LLC (ООО «ХАРЦ Лабс») be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if HARZ Labs LLC (ООО «ХАРЦ Лабс») has been advised of the possibility of such damages.

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ