stomdevice

Tenure®

Multi-Purpose Bonding System

- Tenure A Adhesive 6 mL
- Instruction sheet **(NM-D)**



DenMat®

REF 1145B

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СН

stomdevice

Performance Characteristics

Tenure® is a 4th generation multi-purpose, self-cure adhesive system for bonding any resin restorative to all intra-oral surfaces.

Intended Purpose

Intended to serve as a bonding agent for bonding resin restorative to intra-oral surfaces.

Patient Target Group & Intended Users

- Patients who require dental care such as tooth bonding.
- The intended users are dental professionals.

Expected Clinical Benefits

The clinical benefit would be enhanced oral health.

Qualifications for users

Dental Professional.

CAUTION: Wear protective gloves while using this product.



CAUTION: Wear eye protection while using this product.



CAUTION: Tenure® cannot be used in children, pregnant or breast-feeding women.

INDICATIONS FOR USE

1. All routine direct and indirect resin composite bonding.
2. Porcelain, ceramic veneers, amalgams, precious and semi-precious metals bonding.
3. Indirect gold, porcelain and ceramic inlays and onlays bonding.

INSTRUCTIONS

Enamel and Dentin

1. Remove all caries and/or establish margins of restoration.
2. Apply Etch 'N' Seal® to the enamel and dentin for 10-15 seconds.
3. Rinse thoroughly and dry.
4. Mix equal drops of Tenure A and Tenure B into dappen dish.

*Tenure S Bond Enhancer is recommended for wetting purposes and acts as a final sealer.
Tenure S Filled is recommended for direct composite restorations as it is more viscous.

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ

stomdevice

5. Apply 4 to 6 coats to the tooth surfaces with brush or until glossy in appearance.
6. Allow to fully evaporate, 10-15 seconds.
7. Optional: Apply one thin coat of Tenure S to the surface and light cure.*
8. Proceed with restoration of choice.

Light-cure, starting with:

- 5 seconds - Sapphire® Plus Plasma Arc Curing Light.
- 10 seconds - Flashlite® LED Curing Lights.
- 30 seconds - Conventional Curing Light (e.g., Halogen).

Old Composite/Resin (applies to porcelain and ceramic veneers)

Roughen or sandblast surface. Rinse and dry.
Proceed with steps 4-8.

Metals (applies to amalgams, precious, and semi-precious metals)

Roughen or sandblast surface. Rinse and dry.
Proceed with steps 4-7.
Apply GoldLink®, Geristore®, or Infinity® and restoration of choice.

Contraindications

Patients allergic or hypersensitive to methacrylate monomers.

STORAGE

Do not freeze.
Do not expose to source of ignition or open flame.
Do not expose to temperatures exceeding 77° F (25° C).
Do not expose to direct sunlight.
Bring to room temperature prior to use.

DENMAT CUSTOMER SUPPORT

U.S. and Canada 800-433-6628
U.S. and Canada Fax Orders and Inquiries 800-233-6628
International Inquiries 805-347-7990
International Fax Orders and Inquiries: 805-347-7983
Website ..... denmat.com

SAFETY DATA SHEETS AVAILABLE AT denmat.com

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ

stomdevice

Symbols Glossary available at:
denmat.com/symbols












Den-Mat Holdings, LLC
1017 W. Central Avenue
Lompoc, CA 93436 USA

©2022 Den-Mat Holdings, LLC. All rights reserved. 750412900 R:204/22CM

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ