stomdevice

WXTCERA



HT Pre-Shaded

Preshaded Zirconia Blank
Simple your work flow

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ

stomdevice

Bending Strength	Transmittance	Advantages:
1250 Mpa	43%	High strength & tenacity, wear-proof and stability High-speed operation Anti -aging Properties

Sintering curve

Single crown& Short bridge(within 5 units)

Sintering Steps	Temperature(°C)	Time(h)
Phase 1	20-900	1.5
Phase 2	900-900	0.5
Phase 3	900-1530	3.0
Phase 4	1530-1530	2.0
Phase 5	1530-800	1.5
Phase 6	800-Natural coolingIOO	Finished

Long bridge (more than 5 units)

Sintering Steps	Temperature(°C)	Time(h)
Phase 1	20-900	2.5
Phase 2	900-900	0.5
Phase 3	900-1530	4.0
Phase 4	1530-1530	2.0
Phase 5	1530-800	2.0
Phase 6	800-Natural coolingIOO	Finished

Available shades

A1 A2 A3 A3.5

B1 B2 B3

C2 BL2

Other shades in Vita Classical shades

are available with MOQ request



ShenZhen XiangTong Co., Ltd.

Add: 2nd Floor, 1st building, NO.88, North Zhuguang Rd, West Area, Honghualing Industrial Park, Nanshan District, Shenzhen, China

Tel: +86 755 8600 1804 E-mail: xtcera@xianton.com

Web: en.xtcera.com Facebook: XTCERACHINA

TUVRheinland ISO134M2O10 CE 0197 CFDA FDA Cleared

https://stomdevice.ru - стоматологическое и зуботехническое оборудование с доставкой по России и СНГ